

PRODUCT DATA SHEET

Recycled nylon taslon	Reference Standard/ Test Method
R-XY-010	
150cm (+2/-1cm)	ISO 22198:2006
205gsm (±5)	ISO 3801:1978
100%RPA6	
Taslon	
Green	
waterproof	
≤±3%	ISO 5077:2007 After 5 * Cleaning Cycles at 40°C
Not Detectable	ISO 14184.1:2011
6.14	ISO 3701:2005
4	ISO 105-C06:2010
4	ISO 105-E04:2013
4	ISO 105-X12:2016
3-4	ISO 105-X12:2016
4-5	ISO 12945-1:2000
40 X O P	EN ISO 6330:2013, 4N 40°C
	fabric R-XY-010 150cm (+2/-1cm) 205gsm (±5) 100%RPA6 Taslon Green waterproof ≤±3% Not Detectable 6.14 4 4 4 4 4 4 4 4 4 4 4 4

CONTACT US AT:

SYNERTEX MATERIAL TECHNOLOGY

Room 308, Zone 1, Building B, No. 6433, Yinggang East Road, Zhaoxiang Town, Qingpu District, Shanghai China, 201705

Phone: +86 21 6976 1398 Email: info@synertexmaterial.com

Website: www.synertexmaterial.com; www.recycledprotectivefabrics.com

All the data listed in the above table are either individual test results or the most typical indicative parameters to the best of our knowledge. Owing to existiance of possible vairation or deviation from case to case, the data and information shown in the table is only fo your reference. However, Synertex Material Technology assumes no liability for the accuracy or completeness of the information.